

CLAIMS:

1. A filled halobutyl elastomer composition comprising at least one halobutyl elastomer, at least one mineral filler and at least one protected thiol modifier.
5
2. A filled halobutyl elastomer composition according to claim 1 wherein the halobutyl elastomer is a Bromobutyl elastomer.
3. A filled halobutyl elastomer composition according to claim 1 or 2 wherein the mineral filler is silica.
- 10 4. A filled halobutyl elastomer composition according to any of claims 1 to 3 wherein the protected thiol modifier(s) is/are blocked mercaptosilane(s).
5. A filled halobutyl elastomer composition according to any of claims 1 to 4 wherein the protected thiol modifier(s) is/are thioacetic acid
15 S-trimethoxysilyl-methyl ester, thioacetic acid S-triethoxysilyl-methyl ester, thioacetic acid S-(2-trimethoxysilyl-ethyl) ester, thioacetic acid S-(2-triethoxysilyl-ethyl) ester, thioacetic acid S-(3-trimethoxysilyl-propyl) ester, thioacetic acid S-(3-triethoxysilyl-propyl) ester, thiopropionic acid S-trimethoxysilyl-methyl ester,
20 thiopropionic acid S-triethoxysilyl-methyl ester, thiopropionic acid S-(2-trimethoxysilyl-ethyl) ester, thiopropionic acid S-(2-triethoxysilyl-ethyl) ester, thiopropionic acid S-(3-trimethoxysilyl-propyl) ester, thiopropionic acid S-(3-triethoxysilyl-propyl) ester, thiobutyric acid S-trimethoxysilyl-methyl ester, thiobutyric acid S-triethoxysilyl-methyl ester,
25 thiobutyric acid S-(2-trimethoxysilyl-ethyl) ester, thiobutyric acid S-(2-triethoxysilyl-ethyl) ester, thiobutyric acid S-(3-trimethoxysilyl-propyl) ester, thiobutyric acid S-(3-triethoxysilyl-propyl) ester, pentanethioic acid S-trimethoxysilyl-methyl ester,

pentanethioic acid *S*-triethoxysilyl-methyl ester, pentanethioic acid *S*-(2-trimethoxysilyl-ethyl) ester, pentanethioic acid *S*-(2-triethoxysilyl-ethyl) ester, pentanethioic acid *S*-(3-trimethoxysilyl-propyl) ester, and pentanethioic acid *S*-(3-triethoxysilyl-propyl) ester or mixtures thereof.

5

6. A process for preparing a filled halobutyl elastomer which comprises admixing at least one halobutyl elastomer, at least one mineral filler, at least one protected thiol modifier and at least one cross-linking agent, and curing the resulting filled brominated butyl elastomer.

10

7. In a method of improving the abrasion resistance of a filled, cured elastomer composition comprising at least one halogenated butyl elastomer by admixing said halogenated butyl elastomer with at least one protected thiol modifier.